



CHOICE BRANDS  
A D H E S I V E S  
www.choicebrands.com

## PRODUCT DATA SHEET

CHOICE BRANDS ADHESIVES, 666 REDNA TERRACE #500, CINCINNATI, OH 45215 513-772-1234

**Product:** CBA-502 Crosslinking Hot Press Adhesive

**Description:** Vinyl Acetate Emulsion (PVA)

### Typical Physical Properties:

<b>Solids:</b> 48% +/- 2%	<b>Open Time:</b> 4 - 8 minutes
<b>Viscosity:</b> 5000 cps +/- 1500 cps	<b>Closed Time:</b> Approx 20 minutes
<b>Coverage Rate:</b> 6 – 8 wet mls	<b>Cold Press Time:</b> 40 – 60 minutes
<b>Color:</b> White	<b>Clean Up:</b> Warm soapy water
<b>Shelf Life:</b> One year in unopened container	<b>Coverage:</b> 225 sq ft/gal
<b>Chalk Temperature:</b> 54°F	<b>Packaging:</b> 5, 55, 275 gal containers

**OTC and SCAQMD compliant**

**Certified Leed NC and CI Credit 4.4:** *Laminating Adhesives shall contain no added urea formaldehyde resins*

### SUGGESTED USE:

- Crosslinkable polyvinyl acetate emulsion that is pre-catalyzed and formulated to be ready for use.
- Can be used in a cold or hot press and can be used in RF gluing applications
- Used in an automated glue spreader or manually applied.
- Excellent machinability and stability

### APPLICATION (Cold and Hot Press)

- Substrates must be acclimated to at least 65 deg F – ideally 70 – 85 deg for best results
- Make sure substrates are clean, free of dust or contaminants.
- Use dual durometer roller (Black Bros. #2158 16 x 1/2" pattern)
- Apply 6 – 8 wet mls with glue spreader or roller to board
- Open time is about 4 – 8 minutes
- Closed time is 15 – 20 minutes
- Cold Press is 40 – 60 minutes at 40 – 50 psi
- Wait till board is cool to do any machining in hot press applications

NOTICE TO PURCHASER: The information, data and suggestions for use of the materials given here are based on our best experience and knowledge, but we do not guarantee the results to be obtained in customer's processes. The products discussed are sold without any warranty regarding merchantability or fitness for a particular purpose or any other warranty express or implied. Before using, user shall determine the suitability of the product for his intended use, and user assumes all risk and liability whatsoever in connection therewith. Neither seller nor manufacturer shall be liable for any injury, loss or damage, direct or consequential, arising out of the use of or the inability to use the product. Sellers and manufacturers only obligation shall be to replace such quantity of the product proved to be defective. Since the manufacturer of the product described in this technical data sheet has no means of controlling the final use of the product by the consumer or user, it is the responsibility of the immediate purchaser and any intermediate seller or sellers to inform the user of the purposes for which the product may be fit and suitable, and of the properties of the product, including the precautionary measures which must be taken in order to insure the safety of the user and of other third persons and property.



CHOICE BRANDS  
A D H E S I V E S  
[www.choicebrands.com](http://www.choicebrands.com)

## PRODUCT DATA SHEET

CHOICE BRANDS ADHESIVES, 666 REDNA TERRACE #500, CINCINNATI, OH 45215 513-772-1234

### HOT LAMINATION MACHINERY (EVANS #4260 PANEL EXPRESS)

- Apply 6 – 8 mls to single surface
- Oven Dwell time of 1 minute with exit temperature of 150 – 160 deg F
- Each sequential roller to be set at 50 psi
- Allow assembly to cool completely prior to machining

### APPLICATIONS TO AVOID

- Tempered Hardboard products
- Fire retardant treated board materials
- Boards treated to be moisture resistant
- Low pressure melamine surfaces
- Metallic, polyester or painter surfaces

### STORAGE CONDITIONS:

- **DO NOT ALLOW PRODUCT TO FREEZE**
- **DO NOT STORE BELOW 55 DEG F**
- Keep container lid closed when not in use
- Store product off of concrete floors
- Rotate inventory

### CLEAN UP / DISPOSAL

- Clean up with hot soapy water while adhesive is still wet.
- Use mildly ammoniated water to clean up dried material. Clean-up will be difficult
- Rinse water and water used for clean up is RCRA non hazardous
- Dispose of waste water appropriately

### PRECAUTIONS:

**Please refer to the Material Safety Data Sheet for further safety information.**

NOTICE TO PURCHASER: The information, data and suggestions for use of the materials given here are based on our best experience and knowledge, but we do not guarantee the results to be obtained in customer's processes. The products discussed are sold without any warranty regarding merchantability or fitness for a particular purpose or any other warranty express or implied. Before using, user shall determine the suitability of the product for his intended use, and user assumes all risk and liability whatsoever in connection therewith. Neither seller nor manufacturer shall be liable for any injury, loss or damage, direct or consequential, arising out of the use of or the inability to use the product. Sellers and manufacturers only obligation shall be to replace such quantity of the product proved to be defective. Since the manufacturer of the product described in this technical data sheet has no means of controlling the final use of the product by the consumer or user, it is the responsibility of the immediate purchaser and any intermediate seller or sellers to inform the user of the purposes for which the product may be fit and suitable, and of the properties of the product, including the precautionary measures which must be taken in order to insure the safety of the user and of other third persons and property.