



# Hybond®

## PRODUCT DATA SHEET

CHOICE BRANDS ADHESIVES, 666 REDNA TERRACE #500, CINCINNATI, OH 45215 513-772-1234

### Product: HY-88/HY-88R Flammable Contact Adhesive

#### **BENEFITS:**

VOC Free  
Good Open Time (1 hour)  
CAL/SCQAMD Compliant  
OTC Compliant

containers

#### **TYPICAL PHYSICAL PROPERTIES**

Base: Synthetic Rubber  
Flammability: Highly Flammable  
Solids: 37%  
Viscosity: 200 cps  
Color: Clear  
VOC: 0 g/l (EPA method 24)  
Packaging: 5 and 54 gl  
  
Clean Up: 689  
Shelf Life: 1 Year

**Qualifies for LEED®-NC & CI EQ Credit 4.4: *laminating adhesives shall contain no urea formaldehyde***

#### **SUGGESTED USE:**

A VOC free, fast-drying, contact adhesive designed to produce a strong permanent bond in the decorative laminate industry. It can also be used for general purpose applications such as headliners, carpeting & foam fabrication. Its outstanding features include high initial tack, high green strength and long open time. It is also VOC free.

#### **APPLICATION:**

1. Agitate adhesive before use.
2. Substrates should be clean and free of moisture, dirt, oil, and other contaminants.
3. For best results, adhesive and substrates should be allowed to acclimate to room temperature (approximately 60°F or above) before application of adhesive.
4. The adhesive should be applied at approximately 3.0 dry grams per square foot. The adhesive should cover 80% of the surface of the substrate. The coated substrate surface should exhibit a uniform glossy sheen when the adhesive is completely dry. Dull areas indicate insufficient coverage. Adhesive should be re-applied to these areas.
5. When bonding porous substrates, it is advisable to apply two coats of adhesive. The first coat will act as a sealer and prevent excessive absorption of the adhesive into the substrate. After the first coat has dried, apply a second coat. Allow the second coat to completely dry before assembly.
6. Allowing contact adhesive to dry completely before assembly is essential to obtaining a secure, permanent bond. To check for adhesive dryness, press a piece of Kraft paper onto the adhesive surface. If there is transfer of adhesive to the paper, more time is required to let the adhesive dry. If there is no transfer, substrates are ready for bonding.

NOTICE TO PURCHASER: The information, data and suggestions for use of the materials given here are based on our best experience and knowledge, but we do not guarantee the results to be obtained in customer's processes. The products discussed are sold without any warranty regarding merchantability or fitness for a particular purpose or any other warranty express or implied. Before using, user shall determine the suitability of the product for his intended use, and user assumes all risk and liability whatsoever in connection therewith. Neither seller nor manufacturer shall be liable for any injury, loss or damage, direct or consequential, arising out of the use of or the inability to use the product. Sellers and manufacturers only obligation shall be to replace such quantity of the product proved to be defective. Since the manufacturer of the described in this data sheet has no means of controlling the final use of the product by the consumer or user, it is the responsibility of the immediate purchaser and any intermediate sellers to inform the user of the purposes for which the product may be fit and suitable, and of the properties of the product, including the precautionary measures which must be taken in order to insure the safety of the user and of other third persons and property.



# Hybond®

## PRODUCT DATA SHEET

CHOICE BRANDS ADHESIVES, 666 REDNA TERRACE #500, CINCINNATI, OH 45215 513-772-1234

7. If areas exist with excessive adhesive deposition, twist the (gloved) fingers while pressing them onto the adhesive layer. This will break any film that has formed as the adhesive dries from the top surface down. If a skin has been formed, allow more time for evaporation to ensure complete removal of solvent before bonding. 8. Dry times can be improved through the use of air movement, drying ovens, lamps, etc.

9. Substrates may be indexed together and bonded once the adhesive is dry. Bonds must be made within the open time of the adhesive. (open times may vary by adhesive-see specification on page 1).

10. Uniform pressure on the bonded laminates is necessary to create strong, lasting bonds. 40 pounds per linear inch is recommended to insure complete fusion between the two layers of adhesive to be bonded. A pinch roller is ideal for applying uniform pressure. When used properly, a J-roller can also provide adequate pressure for bonding

11. All contact adhesive bonds are immediately able to be routed, trimmed, cut, filed, and machined

### SUGGESTED EQUIPMENT:

	Manual ms		Automatic ms	
	Binks	DeVilbiss	Binks	DeVilbiss
Spray Gun	95, 2001,	A510, MSA510	21,95A	AGX550
Fluid Tip	63ASS	FX	63ASS	FX
Fluid Needle	663A, 563A	FX	263A, 763A	FX
Air Cap	66SD-3	24	66SD-3	24

### STORAGE CONDITIONS:

Store between 60 and 90°F. Do not store in direct sunlight

If exposed to freezing temperatures, return product to room temperature.

**Please Refer To The Material Safety Data Sheet For Further Information.**

NOTICE TO PURCHASER: The information, data and suggestions for use of the materials given here are based on our best experience and knowledge, but we do not guarantee the results to be obtained in customer's processes. The products discussed are sold without any warranty regarding merchantability or fitness for a particular purpose or any other warranty express or implied. Before using, user shall determine the suitability of the product for his intended use, and user assumes all risk and liability whatsoever in connection therewith. Neither seller nor manufacturer shall be liable for any injury, loss or damage, direct or consequential, arising out of the use of or the inability to use the product. Sellers and manufacturers only obligation shall be to replace such quantity of the product proved to be defective. Since the manufacturer of the described in this data sheet has no means of controlling the final use of the product by the consumer or user, it is the responsibility of the immediate purchaser and any intermediate sellers to inform the user of the purposes for which the product may be fit and suitable, and of the properties of the product, including the precautionary measures which much be taken in order to insure the safety of the user and of other third persons and property.