

PRODUCT DATA SHEET

CHOICE BRANDS ADHESIVES. 666 REDNA TERRACE #500. CINCINNATI. OH 45215 513-772-1234

Product Number: XA-2400

Description: Polyvinyl Acetate Wood Adhesive

Typical Physical Properties:

Solids:49% +/-3%Open Time:Approx. 5-8 minutesViscosity:5000 cps +/-1000Closed Time:Approx. 15-20 minutes

Press Time: Approx. 30-45 mins. @ 40psi **Coverage Rate:** 6 – 9 wet mls White VOC: 13.15 g/l (EPA Method 24) Color: **Coverage:** 240 sq ft/gal **Shelf Life:** One year in unopened container **Chalk Temperature:** 50°F **Packaging:** 5, 55, 275 gal containers

OTC and SCAQMD compliant

Qualifies for Leed Points 3.2, 4.1 and 4.4 : Contains no added urea-formaldehyde resins Substrates to Avoid:

Moisture Resistant Boards Tempered Hardwood Products Metallized, polyester or painted surfaces Low Pressure melamine Fire retardant treated board

Clean Up:

Warm soapy water while adhesive is still wet. Used diluted ammonia to clean dried adhesive. Wash water is NRCA non-hazardous

Storage Conditions:

Do not subject to freezing conditions. Insure adhesive and substrates are conditioned above 65° F. Best results are achieved between 70 and 85° F. **Do not store in direct sunlight.**

Limitations:

Do not use when temperature, glue or materials are below 50°F. Freezing may not affect the function of the product but may cause it to thicken. Agitation should restore product to original form.

Precautions:

For consumer or professional use. Keep out of reach of children.

Please Refer To The Safety Data Sheet For Further Safety Information.

NOTICE TO PURCHASER: The information, data and suggestions for use of the materials given here are based on our best experience and knowledge, but we do not guarantee the results to be obtained in customer's processes. The products discussed are sold without any warranty regarding merchantability or fitness for a particular purpose or any other warranty express or implied. Before using, user shall determine the suitability of the product for his intended use, and user assumes all risk and liability whatsoever in connection therewith. Neither seller nor manufacturer shall be liable for any injury, loss or damage, direct or consequential, arising out of the use of or the inability to use the product. Sellers and manufacturers only obligation shall be to replace such quantity of the proved to be defective. Since the manufacturer of the product described in this technical data sheet has no means of controlling the final use of the product by the consumer or user, it is the responsibility of the immediate purchaser and any intermediate seller or sellers to inform the user of the purposes for which the product may be fit and suitable, and of the properties of the product, including the precautionary measures which must be taken in order to insure the safety of the user and of other third persons and property.

1005X