



TECHNICAL DATA SHEET

1055 36th Street SE Grand Rapids, MI 49508 Page 1 of 3
Phone: 616-245-4415 FAX: 616-245-1890 TOLL FREE: 800-878-8704
www.directsupplyinc.com

March 2023

Rod & Clip Bonder Structural Methacrylate Adhesive

1. DESCRIPTION

Rod & Clip Bonder a two-part non sag methacrylate, structural bonding adhesive designed for the structural bonding of rotolocs, grommets, dishwasher mounts, sink clips into natural stone, granite, marble and porcelain counter top products. Combined at a ratio of 1:1, Rod & Clip Bonder has a working time of 4 to 8 minutes and achieves nearly 90 percent of its ultimate strength in 10 to 15 minutes at room temperature curing. Rod & Clip Bonder provides high strength bonds to the above reference surfaces with generally no preparation effort. Rod & Clip Bonder bonds very strongly to steel, stainless steel, and aluminum metals. Rod & Clip Bonder adhesives are NOT UV STABLE, AND WILL YELLOW OVER TIME and must not be used to create imperceptible seams in countertops or for seaming countertops. This yellowing will not affect bond performance, but will affect bond appearance. Due to its high strength, keep groove widths and depths to a minimum, as wide and deep grooves may cause Rod & Clip Bonder to crack the granite upon reacting and shrinking. We are not liable for cracked counter tops due to this effect.

Company Identification: DutchLock Adhesives
1055 36th Street SE
Grand Rapids, MI 49508
Phone: 616-245-4415 FAX: 616-245-1890 TOLL FREE: 800-878-8704
Website: www.directsupplyinc.com sales@directsupplyinc.com

2. CHARACTERISTICS:

Room Temperature Cure	Properties
• Working Time	4 to 8 minutes (at 75°F/ 24°C)
• Fixture Time	10 to 15 minutes (at 75°F/ 24°C)
• Can be Moved In	20 minutes
• Operating Temp.	65°F to 85°F (18°C to 30°C)
• Gap Filling	.375 inches
• Mixed Density	8.1 lbs/gal (.96 g/cc)
• Flash Point	51°F (11°C) – See SDS for more safety information

3. CHEMICAL RESISTANCE:

Excellent Resistance to:	Susceptible to:
• Hydrocarbons	Polar Solvents
• Acids and Bases	Super Strong Acids and Bases
• Vinegar	
• Wine and Condiments	
• Most Household Foods	

4. PHYSICAL PROPERTIES:

Uncured:	Resin	Activator
• Viscosity(cps)	80,000 – 180,000	80,000 – 180,000



TECHNICAL DATA SHEET

1055 36th Street, SE Grand Rapids, MI 49508

Page 2 of 3

Phone: 616-245-4415 FAX: 616-245-1890 TOLL FREE:

800-878-8704 www.directsupplyinc.com

March 2023

- Density (lbs/gal) 8.2 8.0
- Mix Ratio (wt or vol) 1.0 1.0
- Mixer Recommendation Cartridge (400ml): MGQ 08-24T – Square 24 element

White/Clear Mix Tips (1:1)

5. MECHANICAL PROPERTIES:

Tensile Strength (ASTM D638)	Substrate	Results	Failure Type
• Strength, psi	Fiberglass Surfaces	2,500+	Substrate
• Strength, psi	ABS/PVC Sheeting	1,000+	Substrate
• Strength, psi	Steel/Stainless Steel	2,500 – 3,500	Cohesive
• Strength, psi	Aluminum	2,500 – 3,500	Cohesive

6. HANDLING AND APPLICATION:

Rod & Clip Bonder resin (Part A) and activator (Part B) are flammable. Contents include Methacrylate ester and acids. Keep containers closed after use. Wear gloves and safety glasses to avoid skin and eye contact. Wash with soap and water after skin contact. In case of eye contact, flush with water for 15 minutes and get medical attention. Harmful if swallowed. Keep out of the reach of children. Keep away from heat, sparks, and open flames. Do not smoke cigarettes or anything else while handling or near the product. Refer to the Rod & Clip Bonder Safety Data Sheet for more complete safety instruction. To assure maximum bond strength, surfaces must be mated together within the specified working time, and all clamps affixed within that time. Use sufficient material to ensure that the joint is completely filled when parts are mated and clamped. Avoid over clamping parts, which may cause a dry joint or a joint starved of adhesive. All adhesive application, part positioning, fixturing, and clamping should occur before the working time of the adhesive has expired. After the indicated working time, parts must remain undisturbed until the fixture time is completed. Components bonded, adhesive, and shop temperature can have a significant effect on the work and fixture time of the adhesive.

Application of Rod & Clip Bonder adhesive at temperatures between 65°F and 85°F (18°C and 30°C) will ensure proper cure. Temperatures below 65°F (18°C) will slow cure and fixture speed. Rod & Clip Bonder adhesives will still react, but will take longer. Temperatures above 85°F (18°C and 30°C) will increase cure and fixture speeds, and there's a risk that the adhesive will be hardened or too thick to bond materials. The viscosities of Rod & Clip Bonder adhesives are affected by temperature.

NOTE: Because of the curing features of Rod & Clip Bonder adhesives, large amounts of heat are generated when large masses of material are mixed at one time. The heat generated by the exotherm resulting from mixing large amounts of adhesive can result in a boiling of the monomer in the adhesive (methyl methacrylate), resulting in the release of trapped air, steam and volatile gasses. To prevent this, use only enough material as needed for use within the working time for the product, and confine the gap or spread out the material to no more than .50 inches.

7. HANDLING AND STORAGE

The shelf life of Rod & Clip Bonder is twelve (12) months from the date of manufacture based upon continuous storage at room temperature (77°F or 25°C). Storage of Rod & Clip Bonder adhesives in refrigerated compartments will extend the shelf life even more. Do not store Rod & Clip Bonder adhesive or any other adhesives in a refrigerator which has food or lunch products in them. Be sure to bring Rod & Clip Bonder adhesives to room temperature for 24 hours before use, otherwise longer cure and fixture times may be expected. Long-term storage at temperatures above room temperature



TECHNICAL DATA SHEET

1055 36th Street, SE Grand Rapids, MI 49508

Page 2 of 3

Phone: 616-245-4415 FAX: 616-245-1890 TOLL FREE:
800-878-8704 www.directsupplyinc.com

March 2023

will shorten the shelf life of Rod & Clip Bonder adhesives considerably. Storage at temperatures above 100°F or 38°C could



TECHNICAL DATA SHEET

1055 36th Street SE Grand Rapids, MI 49508

Page 3 of 3

Phone: 616-245-4415 FAX: 616-245-1890 TOLL FREE: 800-878-8704

www.directsupplyinc.com

March 2023

shorten the shelf life to less than one month. Rod & Clip Bonder adhesives contain no water, so freezing of the adhesive for short periods is permissible, but is not encouraged.

8. ADDITIONAL INFORMATION

NOTE: Information contained herein is based on tests we believe to be reliable and accurate. It is offered in good faith for the benefit of the consumer. The Company shall not be liable for any injury, loss, or damage in the use or handling of its chemical products since conditions and use are beyond our control. In every case, we urge and recommend the user conduct tests to determine to their own satisfaction that the product is of acceptable quality and suitability for their particular purpose under their own operating conditions. Statements concerning possible use of our products are not intended as recommendations to use our products in the infringement of any patent, or for any particular purpose or application. These products are intended for industrial use only.